

Decorative solvent based opaque synthetic gold topcoat.
For painting wood and metal items such as:
picture frames, mirrors and other decorative items.
For interior use only.



Product Features: Resistant in temperature up to 90°C. Free of lead and chromates.
Do not wipe the paint. Stains will be remained after wiping.
Do not apply in places near to chemicals/acids/bases.

Technical Data:

Product code (SKU): 605-001

Color: Gold

Gloss: Metallic

Calculated coverage *: 13 sqm./liter (in one coat)

Recommended dilution: Tambour Mineral White Spirit (see recommendation in "Application" section)

Drying times: Touch **: 1 hour | Recoat: 24 hours | Final: 24 hours

Shelf life: 24 months

Package size	Quantity per pallet
0.25 liter	1440
0.75 liter	576

Surface preparation and system recommendation:

Metal:

Before application, make sure that the surface to be painted is clean and dry. Remove rust, flaking metal and any other foreign matter with a steel brush and sandpaper and then rinse with Tambour Mineral White Spirit.

Apply one coat of Multi-Purpose Solvent Based Primer and allow drying to a hard coat. Apply two thin coats of Gold Poliur. Where rust cannot be removed by the aforementioned mechanical means, treat the rust with Tambour Rust Converter and then apply 1-2 coats of Multi-Purpose Solvent Based Primer and allow drying to a hard coat. Apply two thin coats of Gold Poliur.

Wood:

For painted wood and decorative items, apply two thin coats of Gold Poliur directly on the old paint (if the old paint is intact and can't be removed). For new wood, smooth the surface with sandpaper and remove dust. Apply one coat of Multi-Purpose Solvent Based Primer and allow drying to a hard coat. Apply two thin coats of Gold Poliur.

Application: Ready to use paint. Mix thoroughly before application and occasionally during application. Apply thin coats of the paint and make sure that the total thickness does not exceed 30-40 μ .
When applied with a roller or a brush: the paint is ready to use.
Air spraying: dilute with 5% of 1-32 Tambour Thinner. Apply in a 4atm pressure.
Airless: dilute with up to 5% of 1-32 Tambour Thinner. Apply in a 4atm pressure and 0.015" nozzle orifice.

Cleanup and storage: Clean work tools with Tambour Mineral White Spirit, immediately after use. Pour a thin layer of mineral white spirit on the remaining paint and close the container tightly to prevent air penetration. Store in a roofed and ventilated place below 30°C.

Cautions: Any work that includes application and use of this product shall be performed according to the applicable Safety, Health and Environmental regulations. The paint is inedible, flammable, keep out of reach of children. Avoid contact with skin and eyes. Use in a well ventilated area only. Avoid inhaling the lacquer or its vapors. Specific information regarding the product is available in the safety manual (MSDS). Wash your hands with water and soap after completing application.

General notes: Do not apply when the wall is wet or when rain is expected for about 72 hours before and after the application and/or the wall temperature is below 10°C and the relative humidity is above 85%. Never mix this material with others when not specifically recommended by us. Achievement of the best desired results is subject to proper application in strict conformance to our instructions and safety measures. Before application, the user should verify that the product is indeed designed for the intended usage and that the surfaces to be painted are properly prepared, and are suitable for the product's application. Data presented here is based on our best knowledge and experience. We reserve the right to update and/or alter it without prior notice. This product should be carefully tied down during transport.

* The actual coverage rate can vary, depending on the surface, the application mode, the painter's skill and weather conditions at the site. Assume approximately 75% of the calculated coverage ability.

** At 25°C and 65% humidity.

Manufactured by Tambour, a company with a quality assurance system that meeting the requirements of Israeli Standards ISO 9001, ISO 18001, ISO 14001 and accredited by the Israel Institute of Standards in compliance with them.